



pinturas de la peña
fábrica de pinturas

SATIN PLASTIC PAINT L/S

Satin Plastic Paint with medium gloss

Page 1 de 3

The SATIN PLASTIC PAINT L/S is a paint based on emulsions of vinyl copolymers, titanium dioxide and the best loads, which confer the following characteristics:

1. Waterproofing high resistance to weather (on vertical walls).
2. Very decorative satin finish, which forms a single body with painted surface.
3. It has a homogeneous finish, joints are not appreciated, leaving no cord where it is applied.

The Satin painting L/S ensures a great impermeability and magnificent decoration, a high resistance to washing, perfect in all environments and climates, indoors or outdoors.

Features



Color	White
Finish	Silky satin
Brightness at 85 °C	>30 %
Specific weight	1,28 +/-0,05 gr./cc.
Viscosity at time of packaging	95 K.U. a 25°C
Fixed matter %	52% +/- 5
Volume solids	40% +/- 5
Performance	5 - 7 m ² /kg per coat depending on the state of surface
Dry film recommended thickness	43-47 micras per coat
Dry-to-touch time	40-60 minutes
Curing time	21 days
Recoat	8 - 10 hours minimum; maximum without limit
Diluent	Clean water
Presentation	Cans of 5, 10 and 18 kg
Conservation	Keep away from the extreme temperatures
COV'S	Cat A/b (legal limit 100 g/l) maximum content 30 g/l

Application

It is also suitable for exteriors and interiors. It can be applied on the typical elements of work: cement, plaster, concrete, brick, stone, etc.

GUIDELINES FOR A CORRECT APPLICATION: agitate the product until it is perfectly homogenized. The surfaces to be painted must be clean, dry and free of dust, grease, saltpeter, etc. If it was painted before check that the previous painting is in good condition and well adhered. If not, clean the bottom thoroughly and prepare with one coat of acrylic fixative (PEÑAFIJ). The first coat should be diluted 15-20% and the second one applies the paint diluted 5-10%, always with clean drinking water. Utensils and stains are cleaned with water. Do not paint below 5 °c or above 35 ° C of ambient temperature and of the substrate or with a relative humidity of more than 80%. It is not advisable to paint with rainy weather or in the hours of maximum heat.

Composition



Distribuidor Oficial de:

Notice: This information is based on the current condition of our knowledge, and is of general character. It describes our products and orientates the user on it application and employment. Due to the big variety, use conditions and supports it must think neither as base or guarantee nor object of responsibility.

www.delapenia.com

Factory and offices



Trofeo
CC100
Compromiso
a la Calidad

Ctra. Orgaz, s/n
Apdo. 25
45400 Mora (Toledo)

t: +34 925 300 409
f: +34 925 341 082
e: info@delapenia.com



Master
Internacional
de Empresas



pinturas de la peña
fábrica de pinturas

SATIN PLASTIC PAINT L/S

Satin Plastic Paint with medium gloss

Page 2 de 3

Water, emulsions, titanium dioxide, calcium carbonates and other loads chosen for this product.

Suitable for domestic use. Keep out of reach of children.

Cautions

- P101 If medical advice is needed, have the container or label handy.
 P102 Keep out of reach of children.
 P103 Read the label before use.
 P501 To eliminate the contents/container according to the current legislation of waste treatment (law 22/2011).

Mixture of: 5-chloro-2-methyl-2h-isothiazol-3-ona [EC No. 247-500-7]; 2-methyl. 2h-Isouthiazol-3-ona [EC No. 220-239-6] (3:1) may cause an allergic reaction.

According to Royal Decree 363/1995 (Directive 67/548/EEC) and Royal Decree 255/2003 (Directive 1999/45/EC), this is not classified as a dangerous product. Security data Sheet available to the professional user who requests it.



Distribuidor Oficial de:

FESTOOL

Notice: This information is based on the current condition of our knowledge, and is of general character. It describes our products and orientates the user on its application and employment. Due to the big variety, use conditions and supports it must think neither as base or guarantee nor object of responsibility.

www.delapenia.com

Factory and offices



Trofeo
CC100
Compromiso
a la Calidad

Ctra. Orgaz, s/n
Apdo. 25
45400 Mora (Toledo)

t: +34 925 300 409
f: +34 925 341 082
e: info@delapenia.com



Master
Internacional
de Empresas



pinturas de la peña
fábrica de pinturas

SATIN PLASTIC PAINT L/S

Satin Plastic Paint with medium gloss

Page 3 de 3



Distribuidor Oficial de:

Notice: This information is based on the current condition of our knowledge, and is of general character. It describes our products and orientates the user on its application and employment. Due to the big variety, use conditions and supports it must think neither as base or guarantee nor object of responsibility.

www.delapenia.com

Factory and offices



Trofeo
CC100
Compromiso
a la Calidad

Ctra. Orgaz, s/n
Apdo. 25
45400 Mora (Toledo)

t: +34 925 300 409
f: +34 925 341 082
e: info@delapenia.com

Master
Internacional
de Empresas

