pinturas de la peña
fábrica de pinturas

HIGH COVER COATING

100% acrylic lining for vertical walls

Smooth acrylic cladding for facades. Waterproof and washable. For the decoration and protection of exterior and interior walls highly exposed to the weather (extreme climates). It can be applied on any typical material in the construction (cement mortars, concrete, fibre cement, stone, brick, gypsum, etc.). Thanks to its formulation, also indicated for indoor application.

Outstanding features:
100% acrylic paint. Outstanding coverage. High weather resistance. Prevents the carbonization of concrete.

Features

Color	White and colors on request
Finish	Matt
Specific weight	1,65 gr./cc. +/-0.05 gr/cc.
Viscosity at time of packaging	118 K.U. +/- 5 to 25 ºC
Fixed matter%	64 % +/-2
Volumen solids %	40 % +/-2
Performance	8 to 12 m^2/l per coat (recommended: 2 coats)
Wet film recommended thickness	60-80 micras per coat
Dry film recommended thickness	25-35 micras per coat (minumum 2 coats, depending on the state of surface)
Drying time	To touch: 30-90 minutes Total drying: 8-10 hours
Curing time	21 days
Recoat	8 -10 houRs minimum, maximum without limit
Diluent	Water
Presentation	Cans of 14 liters
Conservation	Keep away from the extreme temperatures
Adhesion on concrete	3.17 Mpa
Water vapour permeability	High (W1 0,03m)
Opacity in 150 µm wet film	99.8%
COV´S	Cat A/c (legal limit 40 g/l). Content max. 15 g/l

Application

Can be applied: with brush, roller or pistol, applying thin coats and letting dry before applying a second hand; So, until you get a thickness of film of the desired thickness.
For waterproofing and protection against carbonation in facades: it can be applied on materials as diverse as concrete, cement, brick, stone, etc.
The walls where it is to be applied should be clean, dry and free from residues of old paints. It must not be applied at temperatures of less than 5 º C or above 30 º C, nor in anticipation of frost or rainfall immediately to its application. Always apply 2 º C above the dew temperature; as a general rule it will not be painted above 80% relative humidity.
The cleaning of utensils must be done with water.

Distribuidor Oficial de : FESTOOL GRACO

Notice: This information is based on the current condition of our knowledge, and is of general character. It describes our products and orientates the user on it application and employment. Due to the big variety, use conditions and supports it must think neither as base or guarantee nor object of responsibility.

Trofeo CC100 Compromiso a la Calidad

Factory and offices
Ctra. Orgaz, s/n
Apdo. 25
45400 Mora (Toledo)

t: +34 925 300 409
f: +34 925 341 082
e: info@delapenia.com

Master Internacional de Empresas

PREPARATIONS REMARKS:

On all types of supports:
- In case of contamination by mold, fungi, algae or other parasitic elements, proceed as follows:

- Wash with a solution of water and bleach to 10%.
- Rinse with water.
- Allow to dry thoroughly before starting to paint.
- Use anti-mildew products.

- In case of powdery surfaces or paints with lime:
-Prime with PEÑAFIJ (reduced 4 to 1 with water)

- In case of salins efflorescence (saltpeter):
- Brush and wash with 10% hydrochloric acid or 10% zinc sulfate solution.
- Rinse with water.
-Allow to dry thoroughly before starting to paint.

All these operations must be carried out observing the corresponding safety measures.

Composition

100% Acrylic emulsion, white pigments (dioxide), heavy chemical and mechanical resistance and special additives.

Suitable for domestic use. Keep out of reach of children.

Cautions

P101 If medical advice is needed, have the container or label handy.
P102 Keep out of reach of children.
P103 Read the label before use.
P501 Delete the content and/or its container through the selective collection system enabled in your municipality.

EUH208 Contents 2-octil-2H-isotiazon-3-ona.
Mixture of: 5-chloro-2-methyl-2h-isothiazol-3-ona [EC No. 247-500-7]; 2-methyl. 2h-Isothiazol-3-ona [EC No. 220-239-6] (3:1) may cause an allergic reaction.

Distribuidor Oficial de : FESTOOL GRACO

Notice: This information is based on the current condition of our knowledge, and is of general character. It describes our products and orientates the user on it application and employment. Due to the big variety, use conditions and supports it must think neither as base or guarantee nor object of responsibility.

Factory and offices

Trofeo CC100 Compromiso a la Calidad

Ctra. Orgaz, s/n
Apdo. 25
45400 Mora (Toledo)

t: +34 925 300 409
f: +34 925 341 082
e: info@delapenia.com

Master Internacional de Empresas

According to Royal Decree 363/1995 (Directive 67/548/EEC) and Royal Decree 255/2003 (Directive 1999/45/EC), this is not classified as a dangerous product. Safety data sheet available for professional user on request.

Distribuidor Oficial de : FESTOOL GRACO

Notice: This information is based on the current condition of our knowledge, and is of general character. It describes our products and orientates the user on it application and employment. Due to the big variety, use conditions and supports it must think neither as base or guarantee nor object of responsibility.

Factory and offices

Trofeo CC100 Compromiso a la Calidad

Ctra. Orgaz, s/n
Apdo. 25
45400 Mora (Toledo)

t: +34 925 300 409
f : +34 925 341 082
e: info@delapenia.com

Master Internacional de Empresas